



Flame-Resistant Electrical Insulation Laminates

Grades UTS 141 & 1478

- NEMA GPO-2
- High Strength
- Flame-Resistant Meets UL94 V0
- Cost-Effective
- Outstanding Punchability
- Asbestos-Free

Grades UTS 141 & 1478 are NEMA GPO-2 fiberglass-reinforced laminates that meet UL94 V0 flame-resistance standards. They are ideal for applications requiring flame and heat resistance, as well as applications requiring higher retention of properties after heat aging.

Grade UTS 141 is a NEMA Class F material with a temperature index of 130° C Electrical and 130° C Mechanical. Grade UTS 1478 is a NEMA Class F material with a temperature index of 130° C Electrical and 160° C Mechanical.

They are both available in a standard red color. Both grades are easily fabricated, offering an exceptional capability for punching in their thinner thicknesses. Grade 141 is available from $\frac{1}{32}$ through $\frac{1}{16}$ inch thick. Grade 1478 is available from $\frac{3}{32}$ through $\frac{1}{2}$ inch thick.

Grades 141 & 1478 laminates are ideal for a wide variety of applications, including intricate punchings for switches, switch plates, controls, control panels and terminal boards.





Grades UTS 141 & 1478

	UNIT	ASTM/UL Number	Grade UTS	Grade UTS
General Information				
Part Number			1478	141
Standard Color			Red	Red
Mechanical Properties				
NEMA Grade			GPO-2/GPO-2P	GPO-2
Military Specification	–	–	L-P 509/GPO-2	–
Tensile Strength	Psi	D638	8,900	8,000
Tensile Modulus	Psi X 10 ⁶	D638	1.9	1.3
Flexural Strength	Psi	D790	24,600	18,000
Flexural Strength – 130°C	Psi	D790	14,900	6,000
Flexural Modulus	Psi X 10 ⁶	D790	–	1.2
Compressive Strength	Psi	D695	39,000	30,000
Shear Strength	Psi	D732	13,400	14,000
IZOD Impact Strength (notched)	ft.lb./in.	D256	10.7	8.0
Water Absorption	% by wt.	D570	0.6	0.8
Specific Gravity	–	D792	1.8	1.8
Electrical Properties				
Electrical Strength – Perpendicular S/T in Air	Vpm	D149	433	300
Electrical Strength – Perpendicular S/T in Oil	Vpm	D149	567	–
Electrical Strength – Parallel S/S in Oil	kV	D149	51	40
Arc Resistance	Sec.	D495	130	130
IEC Track Resistance (CTI)	V.	UL746A	500+	–
UL High Voltage Track Rate	In./Min.	UL746A	0	–
Permittivity, 60 Hz	–	D150	4.1	4.5
Dissipation Factor, 60 Hz	–	D150	.011	.05
Permittivity, MHz	–	D150	3.9	–
Dissipation Factor, MHz	–	D150	0.10	–
Insulation Resistance	Ohm x 10 ¹²	D257	270	–
Flame Resistance Properties				
UL Subject 94	–	UL94	VO	VO
UL Hot Wire Ignition	Sec.	UL746A	300+	–
UL High Amp Ignition	# Exposure	UL746A	200+	–
Oxygen Index	%O ₂	D2863	36	–
Ignition Time	Min.	–	81	75
Burn Time	Min	–	48	85
Thermal Properties				
Coefficient of Thermal Expansion	In/In/°C x 10 ⁻⁵	D696	2	2
Thermal Conductivity	BTU/HR/Ft ² /In/°F	C177	1.8	–
UL Temperature Index – Electrical	°C	UL 746B	130	130
– Mechanical	°C	UL 746B	160	130
UL Recognition File Number	–	–	E81928	E23525



Röchling Glastic Composites
 4321 Glenridge Road
 Cleveland, OH 44121 USA
 Tel: 216-486-0100
 Fax: 216-486-1091
www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Glastic products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Röchling Glastic Composites. UL® is a registered trademark of Underwriters Laboratories, Inc.

©2007 Röchling Glastic Composites. All Rights Reserved. Printed in USA GL-???? 0307?M